

TECHNICAL DATA SHEET

CALIPER THICKNESS (MM)	GREY /GREY GSM	WHITE /GREY GSM	PE COTED /GREY GSM	STIFFNESS TABER MD	STIFFNESS TABER CD
1	660	680	730	1100	300
1.1	726	748	803	1400	600
1.2	792	816	876	1800	800
1.3	858	884	949	2000	900
1.4	924	952	1022	2400	1000
1.5	990	1020	1095	2800	1300
1.6	1056	1088	1168	3000	1400
1.7	1122	1156	1241	3500	1600
1.8	1188	1224	1314		
1.9	1254	1292	1387		
2	1320	1360	1460		
2.1	1386	1428	1533		
2.2	1452	1496	1606		
2.3	1518	1564	1679		
2.4	1584	1632	1752		
2.5	1650	1700	1825		
2.6	1716	1768	1898		
2.7	1782	1836	1971		
2.8	1848	1904	2044		
2.9	1914	1972	2117		
3	1980	2040	2190		
GREY BOARD	SPECIFICATION	UNITS	TOLERANCES		
CALIPER	SEE MATRIX	MM	3%		
SUBSTANCE	SEE MATRIX	G/M2	5%		
STIFFNRSS	SEE MATRIX	TABER	15%		
MOISTURE CONTENT	7	%	2%		
FLATNESS	0	%	0.2 % to 1.5 %		